



AEROK®

PYROK®

FORMOA®

FORBOND®

PUROK™

TECHNICAL DATA SHEET

FORMOA PRIMER PG

PRIMER PG is a black primer specifically for treating glass with no ceramic frit coating. Applied before Formoa Screen/Formoa 087GP it gives a protective film against UV rays on the bonding surface between the adhesive and the glass

METHOD OF USE

SURFACE PREPARATION: PRIMER PG must be applied on clean and dry glass, free from dust and grease. Glass can be pre cleaned using IPA and allowed to dry for 10 minutes

APPLICATION: The packaging must be kept closed until used. Do not use direct from the original packaging. For correct application **shake the original container/bottle well for 1 minute and ensure the solution is black** before pouring a small quantity into a primer/cleaner application bottle or small container. Lay the PG down in one pass so as to achieve a uniform coating to the desired width to match the vehicle pattern. Allow a drying time of at least 20 minutes and then apply Formoa Screen/Formoa 087GP. The best results are obtained by applying the adhesive within 4 hours of treating the glass with PG. It is therefore advisable not to apply the PG to a surface that cannot be bonded in this time.

Avoid touching the surface that has been treated with PG as contamination from hands or fingers will reduce performance

CONSUMPTION: approx 3-4m² / L

STORAGE STABILITY: 6 months in the original packaging when stored between 5 - 25°C

Discard any surplus material left in application bottle / small container

Remarks: The directives contained in this document are the results of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the matters and substrates and the greater number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments